AMENDMENTS TO THE CLAIMS:

This listing of claims will replace all prior versions, and listings, of claims in the application:

- 1. (Cancelled).
- 2. (Cancelled).
- 3. (Cancelled).
- 4. (Cancelled).
- 5. (Cancelled).
- 6. (Cancelled).
- 7. (Cancelled).
- 8. (Cancelled).
- 9. (Cancelled).
- 10. (Cancelled).
- 11. (Cancelled).
- 12. (Cancelled).
- 13. (Previously Presented) A carpet tile comprising:
- a primary backing having carpet fiber bundles tufted therethrough, the fibers bundles providing a tufted face;
- a precoat locking the tufts in place to prevent easy extraction of individual fibers and providing a relatively smooth back face opposite the tufted face;

BRODEUR et al Appl. No. 09/639,307 April 8, 2004

a reinforcing scrim adjacent the relatively smooth back face and held in place at least in part by said precoat; and

a preformed open mesh fiber reinforced foam layer with foam nodules held in substantially intimate contact with the relatively smooth back face by an adhesive fused at a temperature sufficiently low to preclude collapse of the foam nodules thereby forming a carpet tile substantially void of curling or doming.

14. (Cancelled).

15. (Previously Presented) A carpet tile as recited in claim 13 wherein said fused adhesive comprises a formulation comprising:

PVC Copolymer

100 parts

Plasticizer

50-100 parts

Filler

0-200 parts

a sufficient amount of silicone surfactant to provide a formulation density below 50 pounds per cubic foot, and

a sufficient amount of silicone surfactant to provide a formulation density below 50 pounds per cubic foot, and

a sufficient amount of fumed silica to provide a formulation pre-fusing Brookfield viscosity of about 30,000 – 60,000 centipoise at a spindle speed of 2 rpm.

16. (Previously Presented) A carpet tile comprising:

a primary backing having carpet fiber bundles tufted therethough, the fibers bundles providing a tufted face;

BRODEUR et al . Appl. No. 09/639,307 April 8, 2004

a precoat locking the tufts in place to prevent easy extraction of individual fibers and providing a relatively smooth back face opposite the tufted face;

a reinforcing scrim adjacent the relatively smooth back face and held in place at least in part by said precoat; and

a preformed open mesh fiber reinforced foam layer with foam modules held in substantially intimate contact with the relatively smooth back face forming a carpet tile substantially void of curling or doming, said preformed open mesh fiber reinforced foam layer with foam nodules being held in substantially intimate contact with the relatively smooth back face and fused thereto at a temperature substantially maintaining the foam nodules in a non-collapsed condition by a formulation of said back face comprising:

PVC resin with a K value of 62-75

100 parts

Plasticizer

60-100 parts

Filler

0-250 parts

and substantially devoid of blowing agent.

- 17. (Cancelled).
- 18. (Cancelled).
- 19. (Cancelled).
- 20. (Cancelled).
- 21. (Cancelled).
- 22. (Cancelled).

BRODEUR et al .Appl. No. 09/639,307 April 8, 2004

- 23. (Previously Presented) A carpet tile according to claim 13 wherein said temperature is less than 310°F.
 - 24. (Cancelled).